




# H48-2 Thermal Conductive Pad

Version 4.180220



## Thermal Conductive Pad

H48-2 is a silicone based thermal pad which has been designed for both efficient heat transfer away from critical devices and ease of manufacture. H48-2 can be provided in a range of formats and thicknesses, such as standard sheets, rolls or die cuts.

## Features

- Good thermal conductivity
- Ultra-soft and high compressibility
- Natural tack
- Easy to assemble
- Good insulator
- Shock and vibration absorber

## Applications


Electronic components: IC, CPU, MOS  
 LED, M/B, P/S, Heat Sink  
 LCD, TV, Notebook PC, PC Telecom Device, Wireless Hub, etc.  
 DDR II Module, DVD Applications, Hand-set applications, etc.

## Properties

- ✓ REACH Compliant
- ✓ ROHS Compliant

Property	H48-2	Unit	Tolerance	Test Method
Colour	Dark Red	-	-	Visual
Thickness (Available thickness range)	0.1-10	mm	-	-
	0.012 - 0.7874	inch	-	-
Thermal Conductivity	2.2	W/mK	±0.2	ASTM D5470
Flammability Rating	V-0	-	-	UL 94
Dielectric Breakdown Voltage	5	kV	±0.1/±0.2/±0.3	ASTM D149
Weight Loss	<1	%	±2	ASTM D412
Density	2.43	g/cm <sup>3</sup>	±0.2	ASTM D792
Working Temperature	-45 to 200	°C	-	-
Volume Resistance	>10 <sup>11</sup>	Ohm-cm	-	ASTM D257
Elongation	282	%	-	ASTM D412
Tensile Strength	7	Kgf/cm2	±2	ASTM D412
Hardness	25	Shore A	±5	ASTM D2240
Shelf Life	36	months	-	-

## Thermal Impedance vs Pressure vs Deflection



T-Global Technology Limited  
 1 & 2 Cosford Business Park, Central Park,  
 Lutterworth, Leicestershire LE17 4QU U.K.

Tel: +44 (0)1455 553 510  
 Email: sales@tglobaltechnology.com  
 Web: www.tglobaltechnology.com  
 VAT #: GB 116 662 714





# H48-2 Thermal Conductive Pad

## Standard Weights & Dimensional Tolerance

Size	Weights (g)			
	Thickness (mm)	0.10	0.20	0.30
100x100		2.10	4.20	6.30
150x150		4.73	9.45	14.18
300x300		18.90	37.80	56.70
320x320		21.50	43.01	64.51

## Data



Die-Cut Thickness Tolerances	Thickness (mm)	Tolerance (mm)
	0.3	±0.03
	0.5	±0.05
	0.8	±0.08
	1.0	±0.1
	1.2	±0.12
	1.5	±0.15
	2.0	±0.2
	2.5 - 3.5	±0.25
	4.0 - 4.5	±0.3
	5.0	±0.35
	6.0 - 8.0	±0.4
	9.0	±0.45
10.0	±0.5	
>10.0	±0.5	

\* Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

**NOTICE:** The information contained herein is to the best of our knowledge true and accurate. However, since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology Europe and North America's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.