

H48-6 Thermal Conductive Pad

Version 5.180220

Thermal Conductive Pad

H48-6 is a silicone based thermal interface pad which offers a good combination of low thermal impedance, good compressibility and a high dielectric breakdown voltage. H48-6 is available in numerous different formats such as custom die cuts or standard sheets.

Features

Good thermal conductivity Ultra-soft and high compressibility Natural tack Easy to assemble Good insulator Shock and vibration absorber

Applications

Electronic components: IC, CPU, MOS LED - M/B, P/S, Heat Sink LCD, TV, Notebook PC, PC Telecom Device, Wireless Hub, etc. DDR II Module, DVD Applications, Hand-set applications, etc.


Properties

REACH Compliant

~	ROHS Compliant	
---	----------------	--

Property	H48-6	Unit	Tolerance	Test Method	
Colour	Dark Grey	-	-	Visual	
Thickness (Available thickness	0.3 - 10	mm	-	ASTM D374	
range)	0.0118 - 0.787	inch	-	ASTM D374	
Thermal Conductivity	3.2	W/mK	±0.3	ASTM D5470	
Flammability Rating	V-0	-	-	UL 94	
Dielectric Breakdown Voltage	2	kV/mm	±0.2	ASTM D149	
Weight Loss	<1	%	-	ASTM E595	
Density	2.42	g/cm³	±0.2	ASTM D792	
Working Temperature	-40 to 200	°C -		-	
Volume Resistance	>1011	0hm-cm	-	ASTM D257	
Elongation	130	% -		ASTM D412	
Tensile Strength	8	Kgf/cm ²	-	ASTM D412	
Hardness	30	Shore A	±10	ASTM D2240	
Shelf Life	36	months	_	_	

Thermal Impedance vs Pressure vs Deflection



T-Global Technology Limited 1 & 2 Cosford Business Park, Central Park, Lutterworth, Leicestershire LE17 4QU U.K.

Tel: +44 (0)1455 553 510 Email: sales@tglobaltechnology.com Web: www.tglobaltechnology.com VAT #: GB 116 662 714




Standard Weights & Dimensional Tolerance

	Thickness	Weights (g)											
	(mm)	0.30	0.50	0.80	1.00	1.50	2.00	2.50	3.00	3.50	4.00	4.50	5.00
Size	100x100	7.29	12.15	19.44	24.30	36.45	48.60	60.75	72.90	85.05	97.20	109.35	121.50
	150x150	16.40	27.34	43.74	54.68	82.01	109.35	136.69	164.03	191.36	218.70	246.04	273.38
	300x300	65.61	109.35	174.96	218.70	328.05	437.40	546.75	656.10	765.45	874.80	984.15	1,093.50
	320x320	74.65	124.42	199.07	248.83	373.25	497.66	622.08	746.50	870.91	995.33	1,119.74	1,244.16

Thicknes (mm)	^{is} 5.50	6.00	6.50	7.00	7.50	8.00	8.50	9.00	9.50	10.00
100x10	0 133.65	145.80	157.95	170.10	182.25	194.40	206.55	218.70	230.85	243.00
150x15	0 300.71	328.05	355.39	382.73	410.06	437.40	464.74	492.08	519.41	546.75
300x30	0 1,202.85	1,312.20	1,421.55	1,530.90	1,640.25	1,749.60	1,858.95	1,968.30	2,077.65	2,187.00
320x32	0 1,368.58	1,492.99	1,617.41	1,741.82	1,866.24	1,990.66	2,115.07	2,239.49	2,363.90	2,488.32

Data



	Thickness (mm)	Tolerance (mm)				
	0.3	±0.03				
	0.5	±0.05				
	0.8	±0.08				
	1.0	±0.1				
	1.2	±0.12				
Die-Cut	1.5	±0.15				
Thickness	2.0	±0.2				
Tolerances	2.5 - 3.5	±0.25				
	4.0 - 4.5	±0.3				
	5.0	±0.35				
	6.0 - 8.0	±0.4				
	9.0	±0.45				
	10.0	±0.5				
	>10.0	±0.5				

* Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

NOTICE: The information contained herein is to the best of our knowledge true and accurate. However, since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology Europe and North America's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.